

Property Profile Cr₂O₃/TiO₂ 75/25 - Coating

Product Number:

IKH 7103

Grain Size Distribution

Grain Size	Distribution
27	-45 +22 μm
26	-38 +10 μm
24	-30 +10 μm
23	-25 +5 μm

*other grainsizes on request

Typical Chemical Composition

Cr ₂ O ₃	base
SiO ₂	< 0,1 %
TiO ₂	~ 25,0 %
Fe ₂ O ₃	< 0,1 %
MgO	< 0,1 %
CaO	< 0,1 %
Al ₂ O ₃	< 0,1 %
Cr met.	< 0,1 %

Coating Properties

Hardness: approx. 900 HV 0,3

Applicable up to 500 °C

Spray Parameters

Plasmagenerator	F4
Plasma Gas Ar (SLPM)	40
Plasma Gas H ₂ (SLPM)	8
Current (A)	500
Spray Distance (mm)	120

